



Size (mm)		Chemical Analysis of Raw Dolomite %					
Powder		MgO	CaO	Fe <sub>2</sub> O <sub>3</sub>	Al <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	LOI
<1.0	5-15	17-22 %	< 31.5 %	< 1.0 %	< 0.8 %	< 1.0 %	< 47 %
0-3	15-25						
1-5	25-40						
	40-60						

Chemical Analysis of Calcined Dolomite %					
CaO	MgO	Al <sub>2</sub> O <sub>3</sub>	Fe <sub>2</sub> O <sub>3</sub>	SiO <sub>2</sub>	L.O.I
55.82	38.28	0.11	0.39	0.80	4.61

Lot 214, 2nd Floor, Wisma MPL, Jalan Raja Chulan, 50200, Kuala Lumpur, Malaysia

Tel: +603-20700006 +603-20700009 Fax: +603-20223777

[www.blackgolddiggers.com](http://www.blackgolddiggers.com)